


Quality Management ISO 9001:2000

Codierung: DBERPSILENZIODUOEN  
 Revision: 01  
 Release date: 24.10.2016  
 Page: 1 of 3

## TECHNICAL DATASHEET

### EGGER SILENZIO DUO



### APPLICATION AREA

Underlay material for floating flooring installation of laminate flooring elements (EN13329) and Design+ flooring (EN 16511:2014) on mineral sub floors

### STANDARD DATA

Product	Silenzio Duo		
Material	Modified XPS/PET underlay material with integrated vapor control layer and self adhesive sealing tape		
Color	gold-anthrazit		
Type of delivery	Folding mat		
Packaging	10 m <sup>2</sup> / package	/	42 packages / pallet

### MATERIAL DATA

Parameter	Specification	Tolerance	Test method
Thickness [mm]	1.5	± 5%	EN 823:2013 (CEN TS 16354)
Length [m]	8.5	± 5%	EN 822:2013 (CEN TS 16354)
Width [m]	1.18	± 5%	EN 822:2013 (CEN TS 16354)
Reaction to fire	Efl		EN13501-1
Thermoforming [°C]	n.a.		
Water absorption [%]	n.a.		
Thermal resistance R <sub>λ</sub> [m <sup>2</sup> K/W]	0.04	± 0,003 %	EN 12664
Water vapor diffusion resistance SD [m]	≥ 75		EN 12086 (CEN TS 16354)

## TECHNICAL DATA CONCERNING CEN TS 16354

Description	Pictogram	Parameter	Value	Recommendations according to the EPLF
Impact Sound Reduction		IS [dB]	≤ 17	> 18
Reflected Walking Sound Reduction		RWS	in progress	in progress
Resistance to Large Ball		RLB [mm]	-	≥ 1.200
Compressive Strength		CS [kPa]	≥ 400	≥ 60
Compressive Creep		CC [kPa]	-	≥ 20
Dynamic Load		DL [cycles]	-	≥ 100000
Punctual Conformability		PC [mm]	≤ 1	≥ 0.5

Information: All above mentioned values were determined under laboratory conditions and defined laboratory materials and structures and may with different system flooring components deviate from these test values. For all of them mentioned performance values inaccuracies are possible owing to the testing methods.

The information given above is based on our current state of knowledge and should be used for information of our product application. This should not be taken to as an assurance of certain quality of our products or their use for specific purposes. Subject to change, legal obligations cannot be derived from the information in this document. Existing commercial protective rights are to be observed.

## INFORMATION/ REQUIREMENTS

- **R<sub>λ,B</sub> (Thermal Resistance)**

The thermal resistance is the resistance of a component to the flow of heat or cold.

Heated or cooled floors:

**EPLF-Requirements:** heated floors:  $R \leq 0.15 \text{ m}^2\text{K/W}$   
 cooled floors:  $R \leq 0.10 \text{ m}^2\text{K/W}$

R<sub>λ,B</sub> is calculated by the sum of R<sub>λ</sub> – values of the individual installed components (e.g. laminate + underlay + humidity protective foil) – see the manufacturer’s instructions.

The smaller the R<sub>λ,B</sub> value of the flooring system or the R-value of the underlay, the better suited the flooring system will be for on a heated / cooled subfloor.

Unheated floors:

**EPLF- Requirements:**  $R_{\lambda} \geq 0.075 \text{ m}^2\text{K/W}$

The greater the R-value of the underlay or R<sub>λ,B</sub> of the flooring system, the more marked will be the rise in temperature and the comfort underfoot (thermal insulation properties).

- **SD Water vapour diffusion resistance (SD-Wert)**

**EPLF- Requirements:**  $SD \geq 75 \text{ m}$

The greater the SD value, the more affectively the foil will protect the laminate flooring against damages through raising damp.

- **PC Punctual Conformability**

**EPLF- Requirements: PC ≥ 0.5 mm**

For acoustic and mechanical protection of the laminate flooring smaller uneven areas should be avoided. The underlayment should be able to compensate for minor irregularities, such as screed granules on the ground. The higher the PC value, the better this compensation functions.

Protection with load:

The flooring system is stressed by daily use.

The greater the DL value, the longer the underlay will withstand dynamic demands. (Walking, static load, furniture movement)

- **DL Dynamic Load**

**EPLF- Requirements: DL ≥ 10000 cycles / increased: ≥ 100000 cycles (intensive / lasting use)\***

Dynamic load by walking.

- **CS Compressive Strength**

**EPLF- Requirements: ≥ 10 kPa / increased: ≥ 60 kPa (intensive / lasting use)\***

Compressive Strength through loading.

The greater the CS value, the better the underlay can protect the connecting system (joint education/-break) against separation and cracking.

- **CC Compressive Creep**

**EPLF- Requirements: ≥ 2 kPa / increased: ≥ 20 kPa (intensive / lasting use)\***

Compressive creep through static load (furniture).

The greater the CC value, the better the laminate floor can withstand permanent loading from heavy furniture.

- **RLB Resistance to Large Ball**

**EPLF- Requirements: ≥ 500 mm / increased: ≥ 1200 mm (intensive / lasting use)\***

In order to minimize damage to the surface the system must be able to absorb brief heavy shocks from falling objects.

The better the underlayment can minimize damage to the surface of the flooring.

- **IS Impact Sound**

**EPLF- Requirements: ≥ 14 dB / increased: ≥ 18 dB (intensive / lasting use)\***

Impact sound is the sound generated when walking on laminate flooring, which is sensed in rooms on lower levels.

The greater the IS value, the better the underlay can reduce the transmission of impact sound.

- **RWS Reflected Walking Sound**

**EPLF- Requirements: in development**

A reflected walking sound refers to the sound that occurs and is sensed when walking on laminate flooring in a room.

Test method: in development

For more information, test methods, etc, please see the „Technical Info sheet- New data sheet: Underlay Materials under Laminate Floor Coverings - Test Standards and Performance Indicators“. (<http://www.eplf.com>).

\* (intensive / lasting use)\*= Laminate flooring / class of use 31, 32, 33)